

Silikat-Fassadenfarbe



Product description

Characteristics:

- Mineral facade paint with AquaSmart-Technology
- Intelligent surface water management
- Natural long-term protection against microorganisms
- Highly permeable
- High degree of whiteness
- 1-component silicate paint according to DIN 18363
- Highly permeable
- Good hiding power
- Application on mineral substrates only
- Gloss level: matt
- Preservative-free

Material

Application Area:

For exterior and interior use on good, solid new and old undergrounds such as lime, lime-cement and cement plasters, concrete, fibre cement as well as old silicate and mineral paints. Do not use on dispersion paints or silicone resin paints.

Binding agent:

Silicate with organic stabilizer

Colour:

White

Content of solids:

Approx. 53 %

Specific gravity:

1.49 g/cm³

pH value:

Alkaline approx. 11

Diluting agent:

JONAS Silikat-Grundfestiger

Viscosity:

Slightly thixotropic

Steam diffusion:

Acc. to DIN EN 52615

$S_D = 0,01 \text{ m}$
class V1 (high)

Water absorption coefficient:

$W_{24} \leq 0,1 \text{ kg/m}^2 \cdot \text{h}^{1/2}$
class W3 (low)

Deviations of technical data as a result of tinting are possible.



JONAS Silikat-Fassadenfarbe



Application characteristics

Application:	Brush / roller / spray (airless). Do not apply on sun heated substrates, during strong winds, at high temperatures, extremely high humidity, in fog or rain. Consider the risk of night frost. If necessary, protect the façade with suitable scaffolding-nets or tarpaulins.
Underground:	All mineral substrates which are clean, dry, and solid. Use JONAS Silikat-Grundfestiger as a primer. In case of new plasters wait for 4 weeks before coating. Fluat and rinse with water. Old coatings based on lime, mineral and silicate must be cleaned or if necessary removed. Fix cracks and holes in plasters, let dry completely. Do not use on dispersion substrates. For underground treatment and application VOB, part C, DIN 18363 and the relevant BFS information must be observed.
Coating build-up:	Priming with JONAS Silikat-Grundfestiger. Priming coat: dilute product with 5 - 10 % JONAS Silikat-Grundfestiger. Final coating: use product without dilution.
Spreading rate per coating:	Approx. 200 ml/m ² on smooth underground (if necessary test on the wall).
Application temperature:	At least + 5°C (Degrees Celsius) for air and underground during application and drying.
Drying:	<p>The surface of the coating is dry and can be painted over after 8 - 10 hours (at a temperature of 20 °C and a relative atmospheric humidity of 65 %). High humidity, low temperatures and low air exchange extend the hardening and drying time.</p> <p>In case of adverse weather conditions always take appropriate actions (e.g. rain protection) to protect work areas and freshly painted surfaces.</p>
Tinting:	<p>Product can be tinted with suitable full-tone and tinting colours up to max. 1 % by volume. For use on tinting machine up to 3 % by volume possible. Check compatibility on a case by case basis. Use tinted product immediately after mixing. Advice: Due to the chemical setting process we cannot accept any liability for colour accuracy and spotless drying. Tinting may lead to deviations in the technical data, also with respect to contents of preservatives.</p> <p>Colour stability: weather, humidity, UV-light and accumulations may have an influence on the coating surface. The process of change is dynamic and depends on climate and exposition conditions. The current national regulations, leaflets etc. apply.</p> <p>Colour accuracy: weather conditions and property conditions have an influence on colour accuracy and the uniformity of colour. The following conditions should be avoided:</p> <ol style="list-style-type: none">Irregularly sucking substrateDifferent surface humidity in the substratePatches with different alkalinity and / or ingredients from the substrateDirect sunlight with sharp shadows on the still humid coating <p>Washout of additives: For coatings which are not yet fully dried any water impact, i.e. dew, fog or rain, may wash-out additives from the coating which then build-up on the surface. The extent of this effect differs, depending on the intensity of the colour. This has no influence on the quality of the product. The effect will disappear under normal weather conditions.</p> <p>Product can be tinted about the mixing machine; colour tone stability B, group 1-3 (according to colour tone) according to BFS information No. 26</p>
Cleaning of tools:	Clean with water immediately after use.

JONAS Silikat-Fassadenfarbe



General information

Storage:	Cool, but not freezing.
Shelf-life:	Can be stored for at least 12 months after date of filling (see additional sticker) if stored properly in the unopened original packaging.
Art.No. and description:	18 00 001 JONAS Silikat-Fassadenfarbe
Packaging:	12.5 l / 5 l
Ingredients:	Water glass, special resin dispersion, white pigment, calcium carbonate, water, additives. As a result of tinting, small amounts of preservatives can be added.
Safety:	Please follow the instructions of the safety data sheet.
Labelling:	This product is not classified according to EU regulation No 1272/2008 [CLP].
Special advice:	Protect glass plates, metal, brick, tiles and marble from splashes. Clean contaminated surfaces with water immediately.
GISCODE:	BSW40
VOC content:	EU limit for the product cat. A/c: 40 g/l (2010). This product contains < 40 g/l VOC.
Waste disposal:	Empty containers can be disposed for recycling. Any dried residues of material can be disposed of as construction waste or together with domestic garbage. Containers with liquid material residues must be disposed of according to local regulations. For further information, please contact your local waste authority.
Advice for use and safety acc. to CLP:	Keep out of reach of children. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Wear appropriate respiratory protection (full mask / half mask equipped with filter type A2/P2). Avoid eating, drinking and smoking during use of the product. Ensure good ventilation during and after application. In case of contact with eyes or skin, rinse immediately with plenty of water. Do not empty into drains or water courses. Safety data sheet available on request.